

**Amendment to OPSS 1216, July 2023****1216 TABLE 1 Primer Properties**

Table 1 of OPSS 1216 is amended by deleting it and replacing it with the following:

**TABLE 1  
Primer Properties**

<b>Property</b>	<b>Test Method</b>	<b>Acceptance Requirement</b>
Distillate obtained, expressed as a percentage of total volume to 360°C (%)	ASTM D402	190 °C 25% minimum 225 °C 70% minimum 260 °C 80% minimum 315 °C 92% minimum
Distillate obtained as a percentage of volume of original cutback asphalt, distilled to 360 °C (%)	ASTM D402	Min. 30%
Water Content (%)	ASTM D95	Max. 0.5%
Solubility in trichloroethylene tested on residue from distillation to 360°C (%)	ASTM D2042	Min. 98%
Penetration (100 g/25 °C/5 sec) tested on residue from distillation to 360 °C (0.1 mm)	ASTM D5	25 to 85 (0.1 mm)
Softening Point tested on residue from distillation to 360 °C	ASTM D36	49 to 80 °C
Saybolt Viscosity at 25 °C (seconds)	ASTM D88	50 to 400 seconds

WARRANT: Always with OPSS 1216